



| Technical parameters | Units | Standards | |
|--------------------------|-------------------|----------------|-----------|
| ⊗ Thickness | mm | EN ISO 24346 | 2,70 |
| ⊗ Wear layer | mm | EN ISO 24340 | 0,15 |
| ⊕ Dimensional stability | % | EN ISO 23999 | ±0,20 |
| ⊕ Classification | class | EN 651 | 21 |
| ↔ Width of rolls | m | EN ISO 24341 | 2/2,5/3/4 |
| ↕ Length of rolls | lm | EN ISO 24341 | 18-27 |
| ⚖ Total weight | kg/m ² | EN ISO 23997 | 1,40 |
| ⊖ Residual indentation | max. mm | EN ISO 24343 | 0,35 |
| 🔥 Fire resistance | | EN 13501-1 | Cfl-s1 |
| 🔊 Impact sound reduction | DLw (dB) | EN ISO 717-2 | 16 |
| ☀ Light fastness | grade | EN ISO 105-B02 | 6 |
| 👁 Slip resistance | class | EN 13893 | DS |
| Ⓜ Warranty | year | | 5 |

**SOLVENT
FREE**

**NOI
WAXI**

