

## graboSport PRIMA


Property	Standard	Unit	Result
----------	----------	------	--------

DESCRIPTION			
Surface	-	-	TECH Surface
Backing	-	-	Closed cell double foam
Thickness	EN ISO 24346	mm	4,5
Weight	EN ISO 23997	kg/m <sup>2</sup>	2,8
Width	EN ISO 24341	m	2
Standard roll length	EN ISO 24341	m	20 ± 10%
Maximal roll length	EN ISO 24341	m	25

CLASSIFICATION			
Product specification	Vinyl indoor sports floor. Meets the requirements of EN 14904 on sub-constructions		
Impact sound insulation	EN ISO717-2	dB	21
Thermal resistance	-	m <sup>2</sup> K/W	0,04
Reaction to fire	EN 13501	-	C <sub>f</sub> -s1
Formaldehyde emission	-	-	No formaldehyde
Pentachlorophenol	-	-	No pentachlorophenol

SPORT PROPERTIES			
Friction	EN 13036-4	-	80-110
Shock absorption	EN 14808	%	19
Vertical deformation	EN 14809	mm	0,7
Ball rebound	EN 12235	%	98
Specular gloss	EN 2813	%	< 30

TECHNICAL CHARACTERISTICS			
Dimensional stability	EN ISO 23999	%	± 0,2
Indentation resistance	EN 1516	mm	<0,5
Resistance to rolling load	EN 1569	N	1500
Colour fastness	ISO 105 B02	-	6
Chemical resistance	EN ISO 26987	-	no change
Abrasion resistance	EN ISO 5470-1	mg/1000cycles	< 250

OTHERS		
Limited warranty		10 years
Cleanability		TECH Surface - Easy to clean
Antimicrobial treatment		graboSAN
Environmental attributes	 	No periodic renewal needed; Solvent and heavy metal free